

## What TMA Measurements Can Tell About the Filler Orientation in Injection Molding

Dr. Natalie Rudolph



1 TMA 402 F3 Hyperion® Polymer Edition and the new expansion sample holder on the right

### Introduction

Fillers have long played an important role in the polymer manufacturing industry. First added to decrease prices of materials, they are now mainly used for their other advantages: Fillers can decrease shrinkage, increase stiffness and sometimes improve the appearance. They are further introduced with the objective to create new material properties not possessed by the matrix material, e.g., flame retardancy, or can be enhanced by the filler, e.g., fibers.


An important property to measure how the filled material changes in length when being heated or cooled is the thermal expansion coefficient,  $\alpha$ , or CTE (coefficient

of thermal expansion). Knowledge about this material behavior is required to be able to determine design values such as shrinkage or compatibility between joining partners of the final product.


However, the CTE is sensitive to the orientation of the filler in the molded part. This orientation depends strongly on the flow field, which describes how the material fills the mold. Therefore, different values for the CTE are to be expected in the molded part. This article aims to investigate this assumption. For this study, a low-viscosity PEEK resin with 40 vol% short carbon fibers was injection molded in a plate mold of 80 x 80 mm and 2 mm thickness at Neue Materialien Bayreuth. A film gate was used to get a more uniform flow front and reduce fiber breakage, which could occur through a thinner gate. The material was dried at 150°C for 3 h before injection molding it with a melt temperature of 410°C into a mold at 175°C.

According to the data sheet, the melting point is at 343°C and the glass transition,  $T_g$ , at 143°C. The melt viscosity at 400°C is as low as 300 Pas. The thermal expansion coefficient,  $\alpha$ , is given in Table 2. Typically, the measurements from the data sheet are performed on a dogbone test specimen which are typically molded with a film gate as well. It has a thickness of 4 mm and a total length of 185 mm. Because the filler orientation depends strongly on the flow field, it is likely that the resulting filler orientation will be different in the mold from Neue Materialien Bayreuth and the mold used to determine the properties on the data sheet. Since the thermal expansion coefficient is sensitive to the filler orientation, different values for the CTE are to be expected in the plate and further in different regions of the plate.

## APPLICATIONNOTE What TMA Measurements Can Tell About Filler Orientation in Injection Molding



- 1 a) Coordinate system used for the part, b) Schematic of the velocity profile and fountain-flow effect of polymers  
c) Resulting filler orientation across the part thickness



- 2 a) Sample extraction location, b) Dominant fiber orientation

### How Does the Molten Material Flow into the Mold?

Figure 2 shows a schematic of the sample plate (a) as well as the velocity profile across the thickness of the part as well as the fountain flow at the melt front (b) and the resulting fiber orientation (c).

Due to the velocity gradient, different forces and moments act on the fibers and lead to a characteristic fiber orientation within the part. In the center of the part, the fibers are oriented perpendicular to the flow direction due to extensional and transverse flow. Due to the high shear rates at the wall or frozen layer, the fibers are aligned parallel to the flow. The thickness of this highly oriented layer depends on the frozen layer thickness and the velocity profile.


### How Were the Samples for the Experiment Prepared and Measured?

For the TMA measurements at NETZSCH Analyzing & Testing, samples of 25 x 5 mm were cut from different regions of the plate according to Figure 3 (a) to study the effect of fiber orientation on the thermal expansion coefficient. The expected dominant fiber orientation is depicted in the samples (b).

The samples were measured with the new TMA 402 **F3 Hyperion**® Polymer Edition (Figure 1). After an initial cooling step, the temperature was increased from -70 to 300°C at a heating rate of 5 K/min. The thermal expansion coefficient was calculated using the mean CTE analysis (m. CTE), which computes the slope between two data points. All measurement conditions are summarized in the table 1.

Tab 1. Test conditions

Sample holder	Expansion, made of SiO <sub>2</sub>
Sample load	50 mN
Atmosphere	N <sub>2</sub>
Gas flow rate	50 ml/min
Temperature range	-70 ... 300°C at a heating rate of 5 K/min



4 TMA measurement results of PEEK with short carbon fibers from different part locations; Sample 1 = red; sample 2 = blue; sample 3 = green

### How Does the Thermal Expansion Correlate to the Flow Field?

The results are shown in Figure 4. The blue line is sample 2, the red line sample 1 and the green line sample 3. As expected, the CTE above the  $T_g$  is higher than below the  $T_g$ ; for these samples it is about double. It can be seen that the CTEs of sample 3 are the lowest and sample 2 has the highest values. Sample 1 is in between. The same trend between samples is observable in the  $T_g$ . Sample 2 that is most dominated by the matrix behavior compared to the other samples has the same  $T_g$  of 143°C as listed in the datasheet (measured with a DSC). Sample 1 that shows more effect of the fiber in the CTE has a higher  $T_g$  of 152°C, which indicates the higher stiffness introduced by the fibers. This can be detected in a TMA, because it measures a mechanical response. Sample 3 is strongly dominated by the fibers and therefore, the  $T_g$  is hardly visible and was not analyzed.

Comparing the measurements of the three samples to the values in the datasheet, it can be seen that the

different sample thickness and overall geometry indeed result in different CTE values. The CTE in the flow direction is in all samples higher than in the datasheet. This means that it is very important to obtain CTE values on specimens of similar shape and geometry as the final product. Otherwise, design values such as shrinkage or compatibility between joining partners will get over or under predicted.

From the CTE measurements as well as the theory of fiber orientation in the flow field, the dominant fiber orientation in the samples can be deduced, Figure 3b. It can be seen that due to the thin samples, the effect of the frozen layer seems to be dominant in samples 2 and 3. The majority of the fibers are oriented in the flow direction  $x$ . Therefore, sample 3 yields the lowest CTE (measurement in the flow and in the fiber direction) and sample 2 the highest values (measurement perpendicular to the flow and fiber direction). Sample 1 is in between the two, because the fountain flow effect is still the largest in this area shortly after the film gate and the fiber orientation is still following the circular flow at the melt front.

## APPLICATIONNOTE What TMA Measurements Can Tell About Filler Orientation in Injection Molding

A summary of the resulting  $T_g$ s is presented in table 2.

**Tab 2.** Summary of the resulting  $T_g$ s

	Sample 1 (red)	Sample 2 (blue)	Sample 3 (green)	Manufacturer's datasheet
$T_g$ [°C]	152	143	-	143

### Summary

The study showed the importance of analyzing the coefficient of thermal expansion of filled materials based on the filler orientation, which is influenced by the flow field during injection molding.

### Acknowledgement

We would like to thank Neue Materialien Bayreuth GmbH for providing the samples.

### About Neue Materialien Bayreuth GmbH

Neue Materialien Bayreuth GmbH is a non-academic research company developing various novel materials for lightweight constructions, from polymers and fiber-reinforced composites to metals, including also the processing. They provide application-oriented solutions by optimizing available materials and production processes.

<https://www.nmbgmbh.de/en/>